

Applications:

- Manufacturing of tanks.
- Suitable for pultrusion process
- Structural Items

Properties:

- Medium reactivity
- Good laminating & wetting properties
- Low viscosity
- Low water absorption and Outstanding resistance to hydrolysis

Composition Of The Resin

FARAPOL I 212 is an Unsaturated Polyester Resin based on Isophthalic Acid and Standard Glycols, dissolved in and cross linked with Styrene having capability to be used as a molding resin for Pultrusion Process.

Compatibility: Avoid storing the resin along with Metallic Driers and Peroxides in the same area.

Safety:

Material Safety Datasheets of the product is available on demand.

Product Data¹:

➤ Viscosity Brookfield(cps, @25°C)	470 ± 20
➤ Acid Value(mgrKOH/gr Resin)	15 - 20
➤ Color (gardner)	<2
➤ Specific Gravity	1.11-1.13
➤ Solid Content(%)	62 ± 2
➤ Gel Time(minute, @25°C)	16 ± 2
➤ Peak Temperature(°C, @25°C)	150-180

Storage Conditions:

FARAPOL I 212 is a product sensitive to temperature, light & oxidation. Hence should be stored indoors in dry place at a temperature between 5 and 25°C. Keep always in the original, unopened and undamaged containers. Avoid to keep material Exposed to sunlight.

Stability:

On storage under above mentioned conditions, the stability for FARAPOL I 212 is 6 months.

Supply Modes:

Resin is Supplied in 200 Kg net. steel Drums and Bulk Road Tankers

1 Gel Time, Acid Value, and Viscosity can be adjusted as per customer requirements.



Gel Time Behavior of Resin at Different Temperature:

@18°C	29-32 ´
@25°C	14-18 ´
@30°C	9-12 ´

Gel time measuring formulation used: (Cobalt Octoate Farapol C 901 1%- 1.0phr, Butanox M50 1.0 phr).

Mechanical Properties of Clear Cured Castings:

PROPERTIES ²	TEST VALUE	METHOD
Barcol Hardness	>35	ASTM D2583
Tensile Strength (MPa)	>75	ISO 527-2
Elongation at Break	>3	ISO 527-2
Heat Distortion Temperature (°C)	>85	ISO 75-2
Flexural Strength	>120	ISO 178

Materials used for curing are: (Cobalt Octoate Farapol C 901 1%- 1.0 phr, Butanox M50 1.0 phr). Curing time is 24 Hrs at room Temperature and 3 Hrs at 80°C.

Water Absorption & Linear Shrinkage:

PROPERTIES	TEST VALUE	METHOD
Water Absorption (%)	≈ 0.30	ISO 62- Test Method-1
Linear Shrinkage (%)	≈ 1.5	Internal Method

This test is done on linear sample with dimensions (1 cm × 1 cm × 100 cm).

Note: The laboratory data and results presented herein were obtained through the use of specific methods mentioned and all necessary precautions, high quality lab reagents, and efficient equipment's by FARAPOL JAM CHEMICAL INDUSTRIES. FARAPOL does not guarantee duplication of such results by third parties.

Connect with us:

Tel: +98 21 88875228

Fax: +98 21 88673951

Site: www.farapol.com

Email: info@farapol.com

Pub. No: POL- F-76-33 rev. 02

