

**Applications:**

- Car body putties
- Suitable for vehicle repairs
- Mastics
- Adhesives

**Properties:**

- Amine-accelerated.
- Medium reactivity.
- Good adhesion to metal, wood and mineral substrate.
- Excellent Sanding Properties

**Composition Of The Resin:**

Amine-accelerated Unsaturated Polyester Resin of FARAPOL is based on orthophthalic anhydride and standard glycols, dissolved in and cross linked with styrene having capability to be used as casting resin for car body putties and mastics. Given its suitable reactivity, it also dries at temperatures < 10°C when used with glass fiber mats to form a medium-hard film with a non-stick surface that can be polished.

**Compatibility:**

Avoid storing the resin along with Metallic Driers and Peroxides in the same area.

**Safety:**

Material Safety Datasheets of the product is available on demand.

**Product Data<sup>1</sup>:**

➤ Viscosity Brookfield(cps, @25°C)	500-700
➤ Acid Value	35-40
➤ Color	light brown
➤ Specific Gravity	≈ 1.11
➤ Solid Content(%)	65±1
➤ Gel Time(minute, @25°C)	30-35

**Storage Conditions:**

Amine-accelerated Unsaturated Polyester Resin of FARAPOL is a product sensitive to temperature, light & oxidation. Hence should be stored indoors in dry place at a temperature between 5 and 25°C. Keep always in the original, unopened and undamaged containers. Avoid keeping material Exposed to sunlight.

**Stability:**

On storage under above mentioned conditions, the stability for Amine-accelerated Unsaturated Polyester Resin of FARAPOL is 6 months.

**Supply Modes:**

This Resin is Supplied in 200 Kg net. Steel Drums and Bulk Road Tankers.

*1 Gel Time, Acid Value, and Viscosity can be adjusted as per customer requirements.*



**Mechanical Properties of Clear Cured Castings:**

<b>PROPERTIES</b>	<b>TEST VALUE</b>	<b>METHOD</b>
Barcol Hardness	>30	ASTM D2583
Tensile Strength (MPa)	>40	ISO 527-2
Elongation at Break	>2	ISO 527-2
Heat Distortion Temperature (°C)	>50	ISO 75-2
Flexural Strength (MPa)	>70	ISO 178

*Materials used for curing are: (2.0 phr Benzoyl Peroxide 25%). Curing time is 24 Hrs at room Temperature and 3 Hrs at 100°C.*

**Water Absorption & Linear Shrinkage:**

<b>PROPERTIES</b>	<b>TEST VALUE</b>	<b>METHOD</b>
Water Absorption (%)	≈ 0.20	ISO 62- Test Method-1
Linear Shrinkage (%)	≈ 1.7	Internal Method

*This test is done on linear sample with dimensions (1 cm × 1 cm × 100 cm).*

**Note:** The laboratory data and results presented herein were obtained through the use of specific methods mentioned and all necessary precautions, high quality lab reagents, and efficient equipment's by FARAPOL JAM CHEMICAL INDUSTRIES. FARAPOL does not guarantee duplication of such results by third parties.

Connect with us:

Tel: +98 21 88875228

Fax: +98 21 88673951

Site: [www.farapol.com](http://www.farapol.com)

Email: info@farapol.com